

POLYCOR LP BR

GEL COAT

BRUSH

Date sheet n° : 7100

Updated : 10.10.17

DESCRIPTION

A pre-accelerated gel coat based on modified Isophthalic unsaturated polyester resin.

Cured using MEKP peroxide.

USE AREAS

This product is formulated for use in a variety of industrial composite parts.

APPEARANCE

Product is available in white, off-white and wide range of colours and can be colour matched according to a particular demand.

The product is formulated to assure complete hide in wet film thickness at 500µm. However some bright shades may have a hide slightly lower opacity.

APPLICATION

This gel coat is ready to use by brush application method.

Mix the product slowly but thoroughly for 10 minutes prior to each shift start up. Apply the correct film thickness. A wet film thickness between 300 to 600µm is required ideally working with a brush to ensure a level even thickness of ideally 500µm.

Check that the correct level of MEKP is added. A level of 1,8% w/w is recommended. Do not use more than 3% w/w or lower than 1,2% w/w of MEKP catalyst.

Minimum application temperature : 15°C

This product is not designed for use with a spray gun.

PROPERTIES / ADVANTAGES

The product is easy to use with highly controlled rheological properties providing high resistance to sagging.

This product has good resistance to yellowing over time.

STORAGE / SHELF LIFE

Shelf-life : 4 Months .

When the product is sealed in its original packing, stored indoors away from direct sunlight and direct heat sources and ideally at ambient temperature between 15°C and 25°C .

FEATURES OF LIQUID PRODUCT

Properties	Test method	Conditions	Unit	Typical values
Density	MT-C G 001 O	25°C	g/cm ³	1,10 - 1,28
Solid content	MT-C G 001 C	15mn at 150°C	%	65 - 72
Viscosity	MT-C G 025 V	25°C - Spindle 5 - 5 rpm	mPa.s	20000 - 25000
Thixotropic index	MT-C G 025 V	5/50 rpm		4,0 - 4,7
Gel time	MT-C G 003 R	Catalyst : Low activity catalyst	min	8 - 13
Peak time	MT-C G 003 R		min	15 - 30
Peak exotherm	MT-C G 003 R	(200g - 25°C - 1,8% MEKP)	°C	145 - 170
Film cure	MT-C G 901 R	(500µ - 20°C - 2% MEKP)	min	45 - 80
Sag resistance	MT-C G 901 O		µm - wet	500
Hide	MT-C G 901 Q	Dependant upon colour	µm - wet	500 - 700
Colour	MT-C G 002 L			Depends colour

PROPERTIES OF THE CURED UNREINFORCED RESIN

Properties	Test method	Conditions	Unit	Typical values
H.D.T	ISO 75 - 2A (2013)	16h at 40°C	°C	54
Tensile strength	ISO 527 (2012)	16h at 40°C	MPa	59
Elongation at break	ISO 527 (2012)	16h at 40°C	%	3,8

For all additional information, refer to the Safety Data Sheet n° FP16594 available on our website.

Company subject to the direction and coordination of Specialty Chemicals International Ltd. The information contained in this document (which is to be intended only for explanatory purposes) is correct and accurate and is based on our technical and scientific knowledge and on literature at the date of publication. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing in the information contained in this document shall be deemed to be a warranty or a representation (explicit or implicit) by the manufacturer, and/or taken or construed as infringing of any existing patents. The manufacturer shall not be under any liability or responsibility for any of the information provided under this document or for any errors, omissions or misstatements, even with regard to results to be obtained through the use of the aforesaid information.