

*colorplas.*

# TD Sheet IB12766A

Clear ISO Standard Visc Brushing Gelcoat



Nicholas Parkinson

Colorplas Ltd 10th Oct 2011

TD Sheet IB12766A

Description Clear, isophthalic brushing polyester gelcoat (standard viscosity)  
**The information in this data sheet also applies to pigmented versions of IB12766A**

Product use General purpose, high quality moulding gelcoat  
for hand lay-up in GRP work.

Characteristics For brush application, free from air and can be used  
clear or pre-pigmented with Colorplas high quality  
pigment pastes. The product is free from drainage  
and has excellent weathering properties as well as  
very good water resistance.

Application IB12766A should be used in workshop temperatures  
between 18 - 25°C and requires the addition of 2%  
Medium activity MEKP for a sufficient cure. For best  
results, the gelcoat should be applied to a clean polished  
mould in one even layer 400 – 500 microns  
(0.4 – 0.5 mm thickness). Before use, the temperature of  
the gelcoat should be 18 - 25°C.

**Liquid gelcoat properties**

Appearance Translucent, blue liquid

Liquid properties Thixotropic

Gel time

2% medium activity

MEKP @ 25°C < 15 minutes