

TECHNICAL DATA SHEET

RESIN VINYLESTER

PRODUCT IDENTIFIER

Product Name:	Resin Vinylester 1579112 Rev.0
Revision Date:	24-SEP-2025

Chemical/Physical Nature

Resin Vinylester is a high grade Bisphenol A Urethane Vinylester, dissolved in styrene. The resin is pre-accelerated and thixotropic. Resin Vinylester features medium viscosity and medium reactivity.

Major Applications

Resin Vinylester is specially developed to meet the requirements of hand lay-up and spray-up applications. The resin is recommended for the fabrication of chemical resistant equipment and marine applications.

Principal Properties

Resin Vinylester has excellent wet out and de-aerating properties for easy processing. Compared to conventional Vinylester resins foaming after MEK peroxide addition is highly reduced in Resin Vinylester leading to less air inhibition inside the laminate and on the surface. Due to its urethane incorporation, Resin Vinylester features enhanced thixotropic behavior preventing rinse off inclined mold surfaces and shows an improved compatibility with aramid fiber reinforcements. Resin Vinylester provides low exothermic reaction during cure allowing thick sections to be fabricated in one go, however through cure in thin laminates is favored by excellent curing behavior. Final products made with Resin Vinylester show excellent hydrolysis resistance and good thermal stability. Resin Vinylester is resistant to many aqueous media, acidic salts, alkaline media and hot water. The resin offers an outstanding combination of heat resistance and flexibility.

Approvals

Cured non-reinforced Resin Vinylester conforms to type I310 according to DIN 16946/2. According to EN13121/1 Atlac® 580 ACT is classified group 7B. The resin is certified by Lloyd's Register and Registro Navale Italiano (R.I.Na.) as laminating resin for use in Marine applications.

TECHNICAL DATA SHEET

PRODUCT SPECIFICATIONS UPON DELIVERY

PROPERTY	RANGE	UNIT	TM
Water content	0 - 1000	ppm	2350
Acid value as such	4.0 - 8.0	mg KOH/g	2401
Solids content, IR	49.5 - 52.5	%	2033
Viscosity, 2 s ⁻¹	1000 - 1600	mPa.s	2313
Viscosity, 20 s ⁻¹	500 - 600	mPa.s	2313
Viscosity, 250 s ⁻¹	370 - 430	mPa.s	2313
Time from 25 °C - 35 °C	25.5 - 31.5	Minute	2625
Time from 25 °C - Peak	42.5 - 52.5	Minute	2625
Peak temperature	125 - 155	°C	2625

Remarks

Viscosity measurement: Z2/23°C

Reactivity measurement: 1.5 g Butanox M 50 added to 100 g of resin

PROPERTIES OF THE LIQUID RESIN (TYPICAL VALUES)

PROPERTY	VALUE	UNIT	TM
Flash point	33	°C	2800
Stability, no init., dark, 25°C	3	Month	-

PROPERTIES OF CAST UNFILLED RESIN (TYPICAL VALUES)

PROPERTY	VALUE	UNIT	TM
Density, 20 °C	1110	kg/m ³	-
Tensile strength	83	MPa	ISO 527-2
Tensile E-modulus	3.5	GPa	ISO 527-2
Elongation at break	4.2	%	ISO 527-2
Flexural strength	153	MPa	ISO 178
Flexural E-Modulus	3.55	GPa	ISO 178
Heat deflection temp. (HDT)	115	°C	ISO 75-A
Glass transition temperature (T _g)	132	°C	DIN 53445
Modulus of elasticity in bending	1.7	GPa	DIN 53445

TECHNICAL DATA SHEET

Impact strength-unnotched spec	15	kJ/m ²	ISO 179
Water absorption, 25 °C	0.16	%	ISO R 62
Water absorption, 100 °C	0.22	%	ISO R 117
Barcol hardness	40	Barcol	2604

Curing Conditions

Cured with 1.5 g Butanox M-50 added to 100 g of resin. After 24 h at RT followed by post curing for 3 h at 100 °C.

PROPERTIES OF CAST REINFORCED RESIN (TYPICAL VALUES)

PROPERTY	VALUE	UNIT	TM
Density, 20 °C			
Glass fiber content			
Tensile strength			
Tensile E-modulus			
Flexural strength			
Flexural E-Modulus			
Compressive strength			
Modulus of elasticity in bending			
Impact resist. - unnotched spec			
Linear expansion			
Thermal conductivity			

Curing Conditions

Laminates made with Atlac 580 cured with 0.5 % Accelerator NL 63-10P, 0.5 % Accelerator NL 51P and 1.5 % Butanox M50Glass fiber matt: OCF M 710 or Vetrotex M 113, both 450 g/m² After 24h at RT followed by post curing for 3 h at 100 °C.

Workshop Conditions

Pot life as function of temperature for 200 g of resin with 3.0 g medium reactive MEK-peroxide

TEMPERATURE	POT LIFE	UNIT
15 °C	45	Minute
20 °C	35	Minute
25 °C	20	Minute

TECHNICAL DATA SHEET

POT LIFE & DEVELOPMENT OR BARCOL HARDNESS (TYPICAL VALUES)

Laminates with 3 layers of glass fiber mat (450 g/m²) cured at 23 °C

Pot Life	1.5 weight % MEK- Peroxide	2.0 weight % MEK- Peroxide	Unit
Resin	28	24	Minute
Laminate	42	37	Minute

Cure Time in h	1.5 weight % MEK- Peroxide	2.0 weight % MEK- Peroxide	Unit
1.5	0	0	Barcol
2.0	10	10	Barcol
2.5	20	20	Barcol
3.0	30	30	Barcol
24	40	40	Barcol
48	40	40	Barcol

Barcol hardness determined with Durometer 934 according ASTM D2583

Guidelines Before Use

Before use, the resin should be conditioned at a well defined application dependent temperature (usually 15°C minimum for a MEKP / Co cure). Stir the resin well before use

Storage Guidelines

The resin should be stored in a dark and dry place in original unopened and undamaged packaging at temperatures between 5°C and 30°C. Shelf life is reduced at higher temperatures and the properties of the resin might change during storage. The shelf life of styrene containing Vinylester will be significantly reduced when exposed to light. Store in dark and in 100% light tight containers only. Exposure to direct sunlight should be avoided.

Material Safety

A Material Safety Data Sheet of this product is available on request.

TECHNICAL DATA SHEET

Test Methods

Test methods (TM) referred to in the table(s) are available on request.

DISCLAIMER

The information contained in this document (which is to be intended only for explanatory purposes) is correct and accurate and is based on our technical and scientific knowledge and on literature at the date of publication. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing in the information contained in this document shall be deemed to be a warranty or a representation (explicit or implicit) by the manufacturer, and/or taken or construed as infringing of any existing patents. The manufacturer shall not be under any liability or responsibility for any of the information provided under this document or for any errors, omissions or misstatements, even with regard to results to be obtained through the use of the aforesaid information.

This information is provided in good faith and every reasonable effort is made to ensure that it is accurate and up-to-date. Tricel Composites (GB) Ltd. shall not be liable for any damage arising, directly or indirectly, from the use of the information contained herein. It is issued on the condition that the user will determine the safety and suitability of this product for their purposes before use. Regulations are country-specific and local information should be sought before placing your product on the market.

Tricel Composites (GB) Limited

Unit A, Foxway,
Off Atkinson Street,
Leeds, West Yorkshire,
LS10 1PS.

Tel: +44 (0)113 270 3133

Email: sales@tricelcomposites.co.uk

Tricel Composites (NI) Limited

Unit 4, Milltown Ind. Estate, Greenan
Road. Warrenpoint, Newry
Co. Down,
BT34 3FN.

Tel: +44 (0)284 175 3738

Email: sales@tricelcomposites.co.uk