

TECHNICAL DATA SHEET

TOPCOAT BR NON-SLIP CLEAR

PRODUCT IDENTIFIER

Product Name:	Topcoat BR Non-Slip Clear 1579165 Rev.0
Revision Date:	29-SEP-2025

MAIN CHARACTERISTICS

Description

Clear standard isophthalic brushing polyester slip-resistant topcoat.

Characteristics

Suitable for application by brush or roller to give an even film free from air and drainage. Can be used clear or pigmented, compatible with Llewellyn Ryland Polyester Colour Pastes.

Intended Use

Designed as a clear or pigmentable general purpose slip-resistant topcoat for use in GRP constructions to hide fibre from lamination and/or provide a degree of grip or resistance to slip.

Application

Laminate surfaces may need abrading for best adhesion. Formulated to cure at temperatures > 16°C and needs only the addition of catalyst prior to use. Medium activity methylethyl ketone peroxide (MEKP) is the recommended catalyst at an addition level of 2% by weight to ensure sufficient cure at room temperature. Topcoat BR Clear should be applied to the substrate in one layer of 375-500 pms (microns)/0.375-0.5mm or 460-610g per square metre. Multiple coats are not recommended.

PROPERTIES OF TRICAST 10 & 50 EPOXY RESIN CLEAR PART A

Appearance	Translucent pink liquid
Liquid Properties	Pseudoplastic and thixotropic
Gel time	100gm flocoat, 2% MEKP @ 25°C < 15 minutes

TECHNICAL DATA SHEET

DISCLAIMER

The information contained in this document (which is to be intended only for explanatory purposes) is correct and accurate and is based on our technical and scientific knowledge and on literature at the date of publication. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing in the information contained in this document shall be deemed to be a warranty or a representation (explicit or implicit) by the manufacturer, and/or taken or construed as infringing of any existing patents. The manufacturer shall not be under any liability or responsibility for any of the information provided under this document or for any errors, omissions or misstatements, even with regard to results to be obtained through the use of the aforesaid information.

This information is provided in good faith and every reasonable effort is made to ensure that it is accurate and up-to-date. Tricel Composites (GB) Ltd. shall not be liable for any damage arising, directly or indirectly, from the use of the information contained herein. It is issued on the condition that the user will determine the safety and suitability of this product for their purposes before use. Regulations are country-specific and local information should be sought before placing your product on the market.

Tricel Composites (GB) Limited

Unit A, Foxway,
Off Atkinson Street,
Leeds, West Yorkshire,

Tricel Composites (NI) Limited

Unit 4, Milltown Ind. Estate, Greenan
Road. Warrenpoint, Newry
Co. Down,

TECHNICAL DATA SHEET

LS10 IPS.

Tel: +44 (0)113 270 3133

Email: sales@tricelcomposites.co.uk

BT34 3FN.

Tel: +44 (0)284 175 3738

Email: sales@tricelcomposites.co.uk