

TECHNICAL DATA SHEET

TOPCOAT BR WHITE

PRODUCT IDENTIFIER

Product Name:	Topcoat BR White 1577014 Rev.0
Revision Date:	19-SEP-2025

MAIN CHARACTERISTICS

Description

Topcoat BR White is a pre-accelerated, thixotropic, isophthalic polyester brushing topcoat which is available in a wide range of colours. (The information in this technical data sheet applies to all colour variations).

Product Use

Topcoat BR White is a general-purpose brushing topcoat to aesthetically improve lamination on GRP mouldings.

Liquid Properties

Topcoat BR White is a thixotropic, air free liquid.

Characteristics & Cure

Exhibits effective air release properties as well as water resistance. The Topcoat BR White is designed to be applied for roller or brush applications with a tack free finish.

Gel Time < 15 minutes

(2% medium reactive MEKP @ 25°C)

TECHNICAL DATA SHEET

Mechanical Properties

*(*Properties of the cured unreinforced resin)*

Barcol Hardness – EN59 – 42

Tensile strength I – SO 527 (2012) – 82

MPa Tensile Elongation – ISO 527 (2012) – 4%

Flexural Strength – ISO 178 (2011) – 102 MPa

Flexural Modulus ISO 178 (2011) – 4500 MPa

HDT – ISO 75-2A (2013) – 77°C

Health & Safety

Please refer to separate Material Safety Data sheet. Avoid curing gelcoats in bulk.

Application

Topcoat BR White should be ideally conditioned to a temperature between 18-23°C before use. Workshop & mould temperature should also be in the same temperature range. Gently agitate the topcoat before use and leave to stand for a short period of time to allow the topcoat to regain the thixotropy. Add 1.5 – 2.5% of a general purpose methyl ethyl ketone peroxide (MEKP) to the topcoat for a sufficient cure. Care must be taken to avoid incorporating air into the topcoat when mixing. Apply the topcoat evenly across the mould surface with a target film thickness of 500-800 microns. Always check the wet film thickness.

Post-Curing

For many applications, sufficient post-curing is possible in typical workshop temperatures between 15-25°C. For optimum topcoat performance, parts must be fully post-cured prior to being put into service (24 hours @ 20°C, followed by 48 hours @ 40°C).

Storage & Packaging

Store away from any direct sunlight in the original, factory sealed airtight containers. Avoid storing outdoors. Store below 20°C but freezing conditions must be avoided. The shelf life & properties of the topcoat can be adversely affected by incorrect storage conditions. Only open containers immediately before use & close airtight after use. Use within 4 months of date of manufacture.

TECHNICAL DATA SHEET

DISCLAIMER

The information contained in this document (which is to be intended only for explanatory purposes) is correct and accurate and is based on our technical and scientific knowledge and on literature at the date of publication. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing in the information contained in this document shall be deemed to be a warranty or a representation (explicit or implicit) by the manufacturer, and/or taken or construed as infringing of any existing patents. The manufacturer shall not be under any liability or responsibility for any of the information provided under this document or for any errors, omissions or misstatements, even with regard to results to be obtained through the use of the aforesaid information.

This information is provided in good faith and every reasonable effort is made to ensure that it is accurate and up-to-date. Tricel Composites (GB) Ltd. shall not be liable for any damage arising, directly or indirectly, from the use of the information contained herein. It is issued on the condition that the user will determine the safety and suitability of this product for their purposes before use. Regulations are country-specific and local information should be sought before placing your product on the market.

Tricel Composites (GB) Limited

Unit A, Foxway,
Off Atkinson Street,
Leeds, West Yorkshire,
LS10 1PS.

Tel: +44 (0)113 270 3133

Email: sales@tricelcomposites.co.uk

Tricel Composites (NI) Limited

Unit 4, Milltown Ind. Estate, Greenan
Road. Warrenpoint, Newry
Co. Down,
BT34 3FN.

Tel: +44 (0)284 175 3738

Email: sales@tricelcomposites.co.uk