

TECHNICAL DATA SHEET

TRICURE 11B711A

PRODUCT IDENTIFIER

Product Name:	TriCure 11B711A 1048017 Rev.2
Revision Date:	23-JUN-2026

This is constructional, accelerated, LSE, white, terephthalic, unsaturated polyester resin with colorful curing indicator system.

TriCure 11B711A is manufactured using recycled PET. Every single 220 kg drum of this resin contains an amount of material equivalent to approximately 1,800–2,900 PET plastic bottles, which have been recycled and reused as a raw material.

Application

TriCure 11B711A is designed for production of polyester glass laminates by hand lay-up or spray-up.

Shelf Life

3 months from the date of manufacture.

Storage

TriCure 11B711A should be stored in closed packaging in a dry, cool place, protected from sunlight and suitable for storage of flammable materials at temperatures not exceeding 25°C.

Processing Conditions

The resin should be mixed before use. Minimum temperature of the resin required for processing is 15 °C. Good curing requires ambient temperature above 18°C and low air humidity. The best curing conditions are obtained using 1% MEKP as hardener. It is possible to adjust gel time by varying the amount of hardener, within in the range of 1-2 %. TriCure 11B711A intensifies decreasing the interlayer adhesion, therefore it is necessary to laminate so as not to leave too much resin on the laminate surface that is to be laminated again. If the stoppage in laminating is longer than 24 hours or the resin amount on the laminate is too big, it is necessary to polish (or sand blast) the laminate

TECHNICAL DATA SHEET

surface before laying down the next layer. Finally, curing could be optimized by post-curing at elevated temperatures.

SPECIFICATION

PROPERTIES	TEST METHOD	UNIT	TYPICAL VALUES
Viscosity at 25°	acc. to ISO 3219	mPa s	180 ÷ 230
Gel time at 25°C	acc. to ISO 2535	min	20 ÷ 30
Flexural strength	acc. to ISO 178	MPa	100
Tensile strength	acc. to ISO 527	MPa	60
Tensile modulus	acc. to ISO 527	MPa	3,000
Elongation at break	acc. to ISO 527	%	2
Heat deflection temperature (HDT)	acc. to ISO 75	°C	65
Barcol hardness	acc. to ASTM D 2583-07	°B	40

Gel time with 1 % Luperox® K-IS (MEKP)

Mechanical parameters refer to unreinforced resin cured for 24 hours at room temperature and post-cured for 2 hours at 80 °C.

TECHNICAL DATA SHEET

DISCLAIMER

The information contained in this document (which is to be intended only for explanatory purposes) is correct and accurate and is based on our technical and scientific knowledge and on literature at the date of publication. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing in the information contained in this document shall be deemed to be a warranty or a representation (explicit or implicit) by the manufacturer, and/or taken or construed as infringing of any existing patents. The manufacturer shall not be under any liability or responsibility for any of the information provided under this document or for any errors, omissions or misstatements, even with regard to results to be obtained through the use of the aforesaid information.

This information is provided in good faith and every reasonable effort is made to ensure that it is accurate and up-to-date. Tricel Composites (GB) Ltd. shall not be liable for any damage arising, directly or indirectly, from the use of the information contained herein. It is issued on the condition that the user will determine the safety and suitability of this product for their purposes before use. Regulations are country-specific and local information should be sought before placing your product on the market.

Tricel Composites (GB) Limited

Unit A, Foxway,
Off Atkinson Street,
Leeds, West Yorkshire,
LS10 1PS.

Tel: +44 (0)113 270 3133

Email: sales@tricelcomposites.co.uk

Tricel Composites (NI) Limited

Unit 4, Milltown Ind. Estate, Greenan Road.
Warrenpoint, Newry
Co. Down,
BT34 3FN.

Tel: +44 (0)284 175 3738

Email: sales@tricelcomposites.co.uk